

THIN | SILVERLAM POSTFORMING

High pressure decorative laminates (HPL), less than 2 mm thick, according to EN 438-3:2016, consisting of a surface of decorative paper(s) impregnated with aminoplastic resins and a core made of layers of kraft paper impregnated with phenolic thermosetting resins. All the layers are bonded together with simultaneous application of heat (approximately 150°C) and high specific pressure (> 7 MPa) to obtain a homogeneous non-porous material with increased density. These laminates include the special characteristic of formability and are normally intended for bonding to supporting substrates, normally wood based, to produce panels by the composite manufacturers. Silverlam Postforming is the innovative Arpa HPL able to inhibit the growth of bacteria across its whole surface. It is microbiologically tested and boasts an antibacterial protection system (Bacteria Blocker), even in case of bacteria such as MRSA (Methicillin-Resistant Staphylococcus Aureus) and E-Coli (Escherichia Coli) responsible for several difficult-to-treat infections. Laboratory testing has proven the prevention of bacterial growth. Silverlam Postforming is physiologically safe and hygienic for food contact and environmentally friendly.

		Decor	Plain colours		Printed decors	
		EN 438 classification	HGP	HGP		
		Standard	EN 438-3	EN 438-3		
PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT	VALUES		
SURFACE QUALITY						
Surface quality	EN 438-4	Spots, dirt and similar surface defects	mm ² /m ²	≤ 1		
		Fibres, hairs and scratches	mm/m ²	≤ 10		
DIMENSIONAL TOLERANCES						
Dimensional tolerances	EN 438-2.5	Thickness tolerance	mm	± 0,10 for thickness 0,5 ≤ t ≤ 1,0		
			mm	± 0,15 for thickness 1,0 < t < 2,0		
	EN 438-2.6	Length and width	mm	+ 10 / - 0		
	EN 438-2.7	Straightness of edges	mm/m	≤ 1,5		
	EN 438-2.8	Squareness	mm/m	≤ 1,5		
	EN 438-2.9	Flatness (measured on full-size sheet)	mm/m	≤ 60		
GENERAL PROPERTIES						
Resistance to surface wear	EN 438-2.10	Initial Point	Revolutions	≥ 150	≥ 100	
Resistance to immersion in boiling water	EN 438-2.12	Appearance - Gloss Finish	Rating	≥ 3		
		Appearance - Other finish	Rating	≥ 4		
Resistance to water vapour	EN 438-2.14	Appearance - Gloss Finish	Rating	≥ 3		
		Appearance - Other finish	Rating	≥ 4		
Resistance to dry heat (160°C/20')	EN 438-2.16	Appearance - Gloss Finish	Rating	≥ 3		
		Appearance - Other finish	Rating	≥ 4		
Resistance to wet heat (100 °C/20')	EN 438-2.18	Appearance - Gloss Finish	Rating	≥ 3		
		Appearance - Other finish	Rating	≥ 4		
Dimensional stability at elevated temperatures	EN 438-2.17	Cumulative dimensional change	Longitudinal %	≤ 0,55		
		Cumulative dimensional change	Transversal %	≤ 1,05		
Resistance to impact with small diameter ball	EN 438-2.20	Spring force	N	≥ 20		
Resistance to impact with large diameter ball	EN 438-2.21	Drop height	mm	≥ 800		
		Indentation diameter	mm	≤ 10		
Resistance to cracking under stress	EN 438-2.23	Appearance	Rating	≥ 4		
Resistance to scratching	EN 438-2.25	Appearance	Rating	≥ 3		
Resistance to staining	EN 438-2.26	Appearance - Group 1 & 2	Rating	≥ 5		
		Appearance - Group 3	Rating	≥ 4		
Light fastness (Xenon-arc)	EN 438-2.27	Contrast	Grey scale rating	≥ 4		
Electrostatic properties	EN 61340-4-1	Point to point resistance	Ω	10 ⁹ ± 10 ¹¹		
		Vertical resistance	Ω	10 ⁹ ± 10 ¹¹		
Formability	EN 438-2.32	Radius	L (parallel to fibre direction) mm	≤ 10 x times nominal thickness		
		Radius	T (right angles to fibre direction) mm	≤ 20 x times nominal thickness		
Resistance to blistering	EN 438-2.34	Time to blister	Seconds - nominal thickness < 0,8 mm	≥ 10		
		Time to blister	Seconds - nominal thickness ≥ 0,8 mm	≥ 15		
Density	EN ISO 1183	Density	g/cm ³	≥ 1,35		
FIRE PERFORMANCES						
Reaction to fire	The reaction to fire of Silverlam Thin Postforming is related to the final composite panel where the laminate is bonded to a substrate. Since the test results also depend on the substrate, the adhesive and the bonding technique applied, the composite manufacturer is responsible for the correct execution of the test in accordance with the applicable standards and test methods required for the specific application field.					
OTHER PROPERTIES						
Thermal resistance / conductivity	EN 12664	Thermal resistance / conductivity	W/mK	0,2 to 0,5		
Hygiene	NSF	NSF/ANSI 35	passing/not passing	pass		
Formaldehyde emission	EN 717- 1	Chamber method	mg/m ³	0,020 - 0,035		
			ppm	0,015 - 0,030		
	EN ISO 12460-3	Gas analysis	mg/(m ² x h)	0,3 ÷ 0,4		
Volatile Organic Chemical Emissions	Greenguard Certification Low Chemical Emission UL 2818 according to EPA TO-17 e ASTM D 6196 EPA TO-11A e ASTM D 5197	Classification	Class	E1		
		Individual VOCs	TLV	≤ 0,1		
		Formaldehyde	ppm	≤ 0,025		
		Total VOC	mg/m ³	≤ 0,25		
		Total Aldehydes	ppm	≤ 0,05		
Contact with food - Overall migration	EN 1186-3	3% acetic acid 24h at 40°C	mg/dm ²	1,2	1,2	
		50% ethanol 24h at 40°C		1,2	1,3	
Contact with food - Formaldehyde specific migration	EN 1186-14	95% ethanol 24h at 40°C		< 1	1,3	
		isooctane 24h at 40°C		< 1	< 1	
		EN 13130-23	3% acetic acid 24h at 40°C	mg/kg	5,3	6,7
Evaluation of antimicrobial activity	JIS Z 2801	Antimicrobial activity after 24 hours at 35°C	bacterial viability Log reduction % reduction	> 3,6 > 99,9		

Note to digital printing decoratives
For the chemical-physical characteristics of digital printing, the laminates with these decoratives may present a limitation in the applications, such as the repeated and intense contact with water or vapour. Customers are asked to contact the Customer Service Arpa Industriale to evaluate the best solution.

Note to laminates with adhesive protective film
The protective films are designed for temporary surface protection against dirt, scratches and tool marks; they are not designed for protection against corrosion, humidity or chemicals. The laminates covered with the protective film shall be stored in a clean, dry place at room temperature (optimum 20°C), avoiding weathering and UV exposure. The protective film must be removed from the surface of the laminates after the application and before putting into use the finite element. In any case, the removal must be made within six months from the date of shipment by Arpa Industriale. Pay close attention to heating in case of postforming. The Customer has to test the postforming process conditions and carry a trial prior to go in a full scale production. Arpa Industriale cannot be responsible for the misuse of the laminates covered with the protective film, nor for the consequences for non-recommended applications.

Disclaimer
The Product Technical Sheets provide all the technical information relevant to the performance of the product as tested by Arpa Industriale or certified testing agencies. Arpa Industriale maintains the right to change and alter the product composition and production process and thereby the performance characteristics of the product at all times, as reported to the Arpa Industriale website. Customers and end-users of the product are requested to check for the latest technical information regarding the products performance on the website of Arpa Industriale before application. In any case, Arpa Industriale, in every contractual relationship, will refer only to the technical information published on its website. Arpa Industriale will not assume any liability if the end-user or customer refer to any other technical information of the products.